

Majvest® 200 & Majvest 200 SOB

Updated on: 30.05.2023

Reference standart: EN 13859-1 / -2

Distributor: SIGA

Type of application: Facade membrane with/without integrated double adhesive zone for rainproof and windproof outdoors facades.

Instructions: see manual

Construction: 3-layer; functional layer protected on both sides with PP fleece.

Characteristics:

		Standards	Units	Values
Dimensions	length width straightness	EN 1848-2 EN 1848-2 EN 1848-2	m m -	50 1.5 / 3.0 passed
Total weight		EN 1848-2	g/m ²	150
Thickness			mm	0.55
Resistance to tearing (nail shank)	lengthwise crosswise	EN 12310-1	N	180 220
Tensile properties Maximum tensile strength	lengthwise crosswise	EN 12311-2	N/50 mm	315 220
Tensile properties Elongation	lengthwise crosswise	EN 12311-2	%	60 70
Air layer thickness equivalent to diffusion s_d:		EN ISO 12572 (C)	m	0.08
Resistance to water penetration		EN 1928	-	W1
Fire classification		EN 13501-1 VKF	Class BKZ	E 4.1
Tightness against rain			-	passed
Temperature resistance	min. temperature max. temperature	EN 1109	°C	- 40 80
Outdoor weathering				12 weeks